CENTRAL LEATHER RESEARCH INSTITUTE FOOTWEAR TESTING LABORATORY

SHOE DESIGN AND DEVELOPMENT CENTRE

ADYAR, CHENNAI- 600 020, INDIA.

TEST/1019/07-08

TEST REPORT

Pg. (1) of (1) DT: 28.09.2007

M/s. EURO SHOE COMPONENTS PVT LIMITED 478/30-A, CORAMANDEL ROAD SIPCOT.RANIPET 632 403

Tele fax: 04172-247136

E mail: euroshoe@euroshoe.in

Dear Sir.

With reference to your letter dated 21st September 2007, we give below the test report for one sample of TPR sole submitted for physical testing.

Sample ID

TPR Sole, Art : ROGER, Marked as "S - 02"

Conditioning

Test Conducted at 20°C and 65% Rh

S. No	PROPERTY	RESULT	CLRI RECOMMENDATIONS		TEST METHOD
		AND THE PERSON NAMED IN	Soft	Hard	
1.	Density, g/cc	0.94	0.9 - 1	0.98 - 1.06	SATRA TM 134: 1998
2.	Hardness, IRHD (Median)	65	50 - 70	71 - 95	SATRA TM 206: 1999
3.	Abrasion resistance, mm ³ Volume loss	277	Max. 350	Max. 400	SATRA TM 174:1994
4.	Tensile strength, N/mm ² Extension at break, %	4.0 320	Min. 4.0 Min. 300	Min. 6.0 Min. 250	SATRA TM 137:1995
5.	Tear strength N/mm	11.3	Min. 8	Min. 8	SATRA TM 218: 1999
6.	Flexing resistance at 20°C Cut growth rate, mm / kc After 30,000 flexes After 50,000 flexes After 75,000 flexes After 100,000 flexes After 120,000 flexes After 150,000 flexes After 150,000 flexes	0.02 0.03 0.02 0.02 0.02 0.02	Max. 0.1	Max. 0.1	SATRA TM 60 : 1992

All the tested properties of this TPR sole sample are found to be good.

Yours faithfully.

R. lyance **Technical Manager**

CLRI Quality Assurance Scheme

Note 1. This test report is not meant for publicity / Advt.

2. This test report is not meant to be produced before customs / Govt. Officials.

3. This institute shall be indemnified against any dispute arising out of issue of this test report.

4. Test conducted on the submitted sample and this institute is not responsible for sampling.

Tel: 044 - 24911386 Extn. 342. Fax: 044 - 24911589

E mail: rajaramanr@ctrim.org; bndas@ctrim.org; rajaramanrr@gmail.com